

SPECIFICATIONS

TROJAN BETA-Z WOOD SEALER

1. PRODUCT: TROJAN BETA-Z WOOD SEALER

2. MANUFACTURING AND DISTRIBUTOR:

ECO-WARES ® / ENVIROSAFE MANUFACTURING CORP. ®

East Coast Office: 7634-B Progress Circle
Melbourne, FL 32904

West Coast Office: 817 Benton Way
Wenatchee, WA 98801

Web Site: www.eco-wares.com

Web Site: www.envirosafemfg.com

3. PRODUCT DESCRIPTION:

TROJAN BETA-Z WOOD SEALER is manufactured for the safe and effective sealing and preservation of wood products.

4. PRODUCT USES:

For industrial, commercial and residential use. **BETA-Z WOOD SEALER** is a one of a kind product for General Contractors, Waterproofing Contractors, Painting Contractors, paper mills, lumber yards, manufacturing, government agencies and homes.

5. JOB LIMITATIONS:

Apply in good weather when air and surface temperature are above 45 degrees F and surface temperature is at least 5 degrees F above the Dew Point. For optimum application properties, materials should be between 70 degrees F to 90 degrees F prior to application. Maintain unused material in closed containers in protected storage at 40-90 degrees F.

6. SURFACE PREPARATION

Good surface preparation is essential to a satisfactory coating system. Surfaces to be coated should be clean and dry. Remove all dirt, dust, oil, grease, mildew, loose or cracked paint or other contamination. Rinse thoroughly and allow to dry.

7. APPLICATIONS INSTRUCTIONS:

Apply by hand or mechanical sprayer at the rate of 200 sq. ft./gal. Apply one (1) coat. Wash tools, equipment and spills with soap and water as soon as possible. Protective gloves, clothing and goggles should be worn for personal cleanliness and to avoid skin and eye irritation. This product **will NOT ETCH GLASS** however it is better not to get material on the glass to avoid having to scrape it off.

8. TECHNICAL DATA:

PRODUCT PROPERTIES

PROPRIETARY INGREDIENTS: Non-hazardous

STATE: liquid

SOLUBILITY IN WATER: Soluble

SPECIFIC GRAVITY: (H₂O = 1) 1.34 @ 20 C

EVAPORATION RATE: (BAC + 1) Same as water

% SOLIDS BY WEIGHT: 19%

VOC: 52.79

pH: 5.5 – 6.0

8. MSDS SHEETS:

Available upon request.